



# GREEN SILICON CARBIDE

## HIGH PURITY GREEN SILICON CARBIDE FOR ABRASIVE APPLICATIONS

Electro Abrasives, LLC. manufactures Green Silicon Carbide powders by water classification at our state-of-the-art headquarters in Buffalo, NY USA. All chemistry and sizing is controlled to meet exact customer requirements. All Green Silicon Carbide manufactured at Electro Abrasives, LLC meets or exceeds ANSI or FEPA standards for product quality.

### **ABOUT:**

Green Silicon Carbide (SiC) is an extremely hard (Mohs 9.4 / 2600 Knoop) man made mineral that possesses high thermal conductivity and high strength at elevated temperatures (at 1000°C, SiC is 7.5 times stronger than Al<sub>2</sub>O<sub>3</sub>). SiC has a modulus of elasticity of 410 GPa, with no decrease in strength up to 1600°C, and it does not melt at normal pressures but instead dissociates at 2700°C.

### **APPLICATIONS:**

Green Silicon Carbide is extremely pure. It can be manufactured into complex bonded shapes or used as a loose abrasive. Applications/uses include vitrified & resinoid grinding wheels, honing stones, blasting grain/powder, compounds, lapping, polishing and many more.

TYPICAL CHEMICAL ANALYSIS	
SiC	99.0%
SiO <sub>2</sub>	0.4%
Si	0.25%
Fe	0.05%
C	0.2%

TYPICAL PHYSICAL PROPERTIES	
Hardness:	Knoop: 2600 Mohs: 9.4
Melting Point:	Sublimes at 4892°F (2700°C)
Specific Gravity:	3.2 g/cc
Particle Shape:	Blocky, Sharp
Color:	Green

### AVAILABLE SIZES

**Macro:** 14 grit—240 grit

**Micro:** F320 grit - F1500 grit, 0.7 micron

Custom Sizes Available Upon Request



701 Willet Road, Buffalo, NY 14218  
Phone: 716-822-2500  
[info@electroabrasives.com](mailto:info@electroabrasives.com)  
[www.electroabrasives.com](http://www.electroabrasives.com)



U.S. ELECTROFUSED MINERALS, INC.  
600 Steel Street, Aliquippa, PA 15001  
Phone: 800-927-8823  
[www.usminerals.com](http://www.usminerals.com)



GRUPO CURIMBABA

Updated: 05/13

The information contained in this data sheet has been determined through the application of accepted engineering practice and is believed to be reliable. Since the conditions of application and use of our products are beyond our control, no warranty is expressed or implied regarding accuracy of the information, the results to be obtained from use of the product, or that such use will not infringe on any patent. This information is furnished with the express condition that you will make your own tests to determine the suitability of the product for your particular use.