

## MAE-26 - ALUMINA-MAGNESIA SPINEL

## FUSED ALUMINA-MAGNESIA SPINEL FOR REFRACTORIES

## ABOUT:

MAE-26 is a fused Alumina-Magnesia Spinel obtained from fusion of alumina and magnesia in an electric arc furnace. It presents high chemical stability due to its macro crystals. MAE-26 is recommended for refractory applications.

TYPICAL CHEMICAL ANALYSIS		
Al <sub>2</sub> O <sub>3</sub>	73.66%	
MgO	25.43	
SiO <sub>2</sub>	0.11	
Fe <sub>2</sub> O <sub>3</sub>	0.06	
Na <sub>2</sub> O	0.49	

TYPICAL PHYSICAL PROPERTIES		
Crystal Structure:	Spinel	
Melting Point:	2100° C	
Color:	Grey	
Specific Gravity:	3.51 g/cc	
Average Crystal Size:	4,000 μm	
Apparent Porosity:	3.1%	
Apparent Specific Density:	3.25 g/cm <sup>3</sup>	

App. Porosity & App. Specific Density by ASTM C 20-00

AVAILABLE SIZES		
MESH	METRIC (mm)	
3/4" x 5/16"	19.1 - 8.00	
5/16" x 4	8.00 - 4.75	
4 x 10	4.75 - 2.00	
10 x 20	2.00 - 0.850	
10 x 40	2.00 - 0.425	
20 x 40	0.850 - 0.425	
40 x 200	0.425 - 0.075	
TPF II	- 0.212	
200 MF	- 0.075	
325 MF	- 0.045	
*Other sizes available upon request		

The information contained in this data sheet has been determined through the application of accepted engineering practice and is believed to be reliable. Since the conditions of application and use of our products are beyond our control, no warranty is expressed or implied regarding accuracy of the information, the results to be obtained from use of the product, or that such use will not infringe on any patent. This information is furnished with the express condition that you will make your own tests to determine the suitability of the product for your particular use.



600 Steel Street, Aliquippa, PA 15001

Phone: 800-927-8823 email: <u>info@usminerals.com</u> <u>www.usminerals.com</u>



701 Willet Road, Buffalo, NY 14218

Phone: 716-822-2500

Email: <u>info@electroabrasives.com</u> www.electroabrasives.com



GRUPO CURIMBABA

Updated: 04/13